

Zinc and zinc alloys — Primary zinc

The European Standard EN 1179:2003 has the status of a
British Standard

ICS 77.120.60

National foreword

This British Standard is the official English language version of EN 1179:2003. It supersedes BS EN 1179:1996 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee NFE/8, Zinc and zinc alloys, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 22 May 2003

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 7 and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

English version

Zinc and zinc alloys - Primary zinc

Zinc et alliages de zinc - Zinc primaire

Zink und Zinklegierungen - Primärzink

This European Standard was approved by CEN on 5 March 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovak Republic, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents		page
Foreword.....		3
1	Scope	4
2	Normative references	4
3	Terms and definitions.....	4
4	Manufacture.....	5
5	Ordering information	5
6	Requirements	5
6.1	Chemical composition.....	5
6.2	Shape of ingots	5
6.3	Surface condition of ingots	5
7	Sampling and analysis	6
8	Marking and labelling	6
9	Inspection documents	6

Foreword

This document (EN 1179:2003) has been prepared by Technical Committee CEN /TC 209 "Zinc and zinc alloys", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2003, and conflicting national standards shall be withdrawn at the latest by November 2002.

This document will supersede EN 1179:1995.

This is one of a series of European Standards for zinc and zinc alloy products. Other products are specified in the following standards:

EN 988, *Zinc and zinc alloys — Specifications for rolled flat products for building.*

EN 1774, *Zinc and zinc alloys — Alloys for foundry purposes — Ingot and liquid.*

EN 12844, *Zinc and zinc alloys —Castings — Specification.*

EN 13283, *Zinc and zinc alloys — Secondary zinc.*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies the classification, chemical composition, marking and other requirements for primary zinc. The grades of zinc included in the standard are those which are traded internationally. The standard does not include requirements for secondary zinc produced by remelting.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 12060, *Zinc and zinc alloys — Method of sampling — Specifications.*

EN 12441-3, *Zinc and zinc alloys - Chemical analysis - Part 3: Determination of lead, cadmium and copper - Flame atomic absorption spectrometric method*

EN 12441-5, *Zinc and zinc alloys - Chemical analysis - Part 5: Determination of iron in primary zinc - Spectrophotometric method*

EN 12441-6, *Zinc and zinc alloys - Chemical analysis - Part 6: Determination of aluminium and iron - Flame atomic absorption spectrometric method*

3 Terms and definitions

For the purposes of this European Standard, the following terms and definitions apply:

3.1

ingot

cast product intended for remelting

3.2

primary zinc

zinc obtained from the ore, or other zinc-bearing material, by a process of distillation or by chemical or electrolytic reduction

NOTE Primary zinc is normally supplied in ingot form, but may also be available in liquid form.

3.3

cast

3.3.1

cast, for non-continuous casting

product of one furnace, or crucible melt

3.3.2

cast, for continuous casting

identified volume of liquid metal

3.4

batch

number of ingots taken from a single cast

3.5

bundle

collection of ingots taken from a single cast and secured, for example by banding, for the purposes of handling, shipment and storage

3.6

jumbo

large ingot not suitable for manual handling, weighing at least 30 kg. Normally a jumbo weighs several hundred kilogram

4 Manufacture

Zinc ingots shall be manufactured by casting from liquid primary zinc.

5 Ordering information

The following information shall be supplied by the purchaser in the order to assist the supplier in providing the correct material:

- a) the number of this European Standard (EN 1179);
- b) the grade of the primary zinc required (see Table 1);
- c) the total mass required;
- d) for ingots, their individual nominal mass;
- e) when a specific ingot shape is required (see 6.2);
- f) when a certificate of analysis or a declaration of conformity is required (see clause 9).

6 Requirements

6.1 Chemical composition

The primary zinc shall conform to the chemical composition given for the appropriate grade in Table 1.

In expressing the results for the analysis, the values obtained shall be rounded to the same number of decimal places as used in expressing the specified limit in Table 1.

The following rules shall be used for rounding:

- a) if the figure following the last figure to be retained is less than 5, the last figure to be retained shall be kept unchanged;
- b) if the figure following the last figure to be retained is equal to or greater than 5, the last figure to be retained shall be increased by one unit.

6.2 Shape of ingots

The shape of ingots shall be at the supplier's discretion unless a specific shape has been agreed upon between purchaser and supplier and stated in the enquiry and order [see clause 5 e)].

6.3 Surface condition of ingots

The surface condition of ingots shall be such that it does not affect the chemical composition requirements, and is not detrimental to the end use of the ingots.

7 Sampling and analysis

The sampling of primary zinc for verification of its conformity to the chemical composition requirements of this standard shall be in accordance with EN 12060.

The chemical composition given in Table 1 shall, in case of dispute, be determined by wet chemical methods given in EN 12441-3, EN 12441-5, and EN 12441-6, unless otherwise agreed.

NOTE: Optical emission spectrometry analysis, according to EN 12019, is recommended only for production control purposes and end-product certification.

8 Marking and labelling

All ingots or bundles shall be marked, or labelled, with the following minimum information:

- a) the producer's mark;
- b) the zinc grade (by grade classification or by colour code [see Table 1];
- c) the batch or cast reference;
- d) the mass of the ingot or bundle.

9 Inspection documents

If requested by the purchaser at the time of ordering, the supplier shall furnish inspection documents with each consignment. The documentation shall be as chosen by the purchaser [see clause 5 f)] and shall be in accordance with either a) or b), as follows:

- a) a certificate of analysis, giving the results obtained on the specific casts in the consignment;
- b) a declaration of conformity of the consignment with the order requirements. This declaration shall include the following information:
 - 1) name and address of supplier;
 - 2) date of declaration of conformity;
 - 3) name and address of purchaser;
 - 4) purchaser's order number;
 - 5) a description of the goods and the quantity supplied;
 - 6) identification of this standard and the grade supplied;
 - 7) the following declaration:

'The goods detailed hereon have been manufactured to conform to the requirements of the purchaser's order and specification detailed thereon.'

Signature: _____

(supplier's authorized representative)

Table 1 — Chemical composition of primary zinc

Grade classification	Colour code	Composition in % (mass fraction)							
		Nominal zinc content	1	2	3	4	5	6	Total of elements in columns 1 to 6
			Pb max.	Cd max.	Fe max.	Sn max.	Cu max.	Al max.	
Z1	White	99,995	0,003	0,003	0,002	0,001	0,001	0,001	0,005
Z2	Yellow	99,99	0,005	0,003	0,003	0,001	0,002	—	0,01
Z3	Green	99,95	0,03	0,005	0,02	0,001	0,002	—	0,05
Z4	Blue	99,5	0,45	0,005	0,05	—	—	—	0,5
Z5	Black	98,5	1,4	0,005	0,05	—	—	—	1,5

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.